

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999  
 DateRun: 07/06/1999  
 Experimenters: Nicole Vayo  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Greases  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Nine products were used at 5% dilutions and heated to 130 F. Stainless steel coupons were coated with Keystone KSL 111 Synthetic Tacky Grease (64742-47-8). Coupons were rinsed with tap water for 2 minutes.

**Results:**

**Summary:**

<b>Substrates:</b>	Stainless Steel				
<b>Contaminants:</b>	Greases				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Savogran Company	Dirtex Prepaint Cleaner	5	99.00	<input checked="" type="checkbox"/>	
EcoLink	Universal Steam Cleaner	5	29.00	<input type="checkbox"/>	
Heatbath Corporation	Multi-Kleen 1568	5	99.00	<input checked="" type="checkbox"/>	
Warren Chemical Company	Sea Wash Neutral	5	99.00	<input checked="" type="checkbox"/>	
MacDermid Industrial Products	New Dimensions LF Supreme	5	98.00	<input checked="" type="checkbox"/>	
Man Gill Chemical Company	Gillite 160 X	5	91.00	<input checked="" type="checkbox"/>	
Master Chemical Corporation	Trim Rinse 100	5	72.00	<input type="checkbox"/>	
Novamax Technologies Inc	Spectrum APC	5	95.00	<input checked="" type="checkbox"/>	
International Bio System	Bio Z	5	91.00	<input checked="" type="checkbox"/>	

**Conclusion:** Multikleen LX 1573 removed 98% of the grease