

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 08/30/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Paints

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Paint, Painter Touch Blue, CAS: 67-64-0, 1330-20-07

Results:

Summary:

Substrates:		Aluminum				
Contaminants:		Paints				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	
Savogran Company	SI #4 Coating Remover	100	-4.65	<input type="checkbox"/>		
Gemtek Products	SC Supersolve Safety Solvent	30	5.62	<input type="checkbox"/>		
Twin Rivers Technologies	Methyl Ester 1618	100	87.80	<input checked="" type="checkbox"/>		
Invista S.a.r.l	Flexisolv DBE 4 ester	100	89.30	<input checked="" type="checkbox"/>		

Conclusion: