

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 11/08/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Lubricating/Lapping Oils

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Lubricant, Lubri Temp Anti Seize

Results:

Summary:

Substrates:		Stainless Steel			
Contaminants:		Lubricating/Lapping Oils			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Brulin Corporation	Compliance	10	-27.90	<input type="checkbox"/>	
AW Chesterton	278 Super Solv	10	14.50	<input type="checkbox"/>	
US Polychem Corporation	87 RB	100	93.70	<input checked="" type="checkbox"/>	
Bio Chem Systems	Bio T Max	100	88.60	<input checked="" type="checkbox"/>	
Transene Company, Inc.	D Greeze 500 LO	100	91.00	<input checked="" type="checkbox"/>	
Warren Chemical Company	Sea Wash 8	5	-40.60	<input type="checkbox"/>	
Ensolve Biosystems Inc	Grease Feast Plus	5	4.90	<input type="checkbox"/>	

Conclusion: