

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003

DateRun: 09/09/2003

Experimenters: Jason Marshall

ClientType: Lab

ProjectNumber: Project #1

Substrates: Brass

PartType: Coupon

Contaminants: Buffing/Polishing Compounds

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Four products were used at full strength, heated to 120 F on a hot plate. Twelve preweighed coupons were coated with Jackson Lea Antique Buffing Compound LM 12 (9000-70-8, 1344-28-1, 409-21-2, 1309-37-1) and allowed to dry overnight and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry overnight and then reweighed a final time. Efficiencies were calculated.  
Note: Bio T Foam Plus was sprayed onto coupons at room temperature and allowed to sit for 5 minutes. The cleaner was then wiped clean.

Results: Two products removed over 95% of the buffing compound and a third removed over 85%.

Summary:

<b>Substrates:</b>		Brass			
<b>Contaminants:</b>		Buffing/Polishing Compounds			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
AW Chesterton	278 Super Solv	100	95.63	<input checked="" type="checkbox"/>	
Bio Chem Systems	Bio T Foam Plus	100	95.61	<input checked="" type="checkbox"/>	
Invista S.a.r.l	Flexisolv DBE Ester	100	88.59	<input checked="" type="checkbox"/>	
Gemtek Products	SC EZ Solv Safety Solvent	100	52.56	<input type="checkbox"/>	

Conclusion: AW Chesteron 278 Super Solv, Bio Chem Systems Bio T Foam Plus and DuPont DBE were all effective.