

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004

DateRun: 07/07/2004

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Sterling/Silver

PartType: Coupon

Contaminants: Oil

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Cleaning: 5 min. immersion cleaning at 96 F with stir-bar agitation.
NO Rinsing
Drying: 30 sec. Air blow off using hose and outlet on bench
Contaminant:
Oil - Exxon Mobile Vacimul O3D Cas# 64741-44-2
Substrate 2 " x 2" Silver plated copper

Results:

Summary:

Substrates:	Sterling/Silver				
Contaminants:	Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Petroferm Inc	Lenium CP (no longer available)	100	99.40	<input checked="" type="checkbox"/>	
Petroferm Inc	Lenium ES	100	98.65	<input checked="" type="checkbox"/>	
Invista S.a.r.l	Flexisolv DBE 6 ester	100	100.13	<input checked="" type="checkbox"/>	

Conclusion: All were effective.