

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2005  
 DateRun: 06/27/2005  
 Experimenters: Jason Marshall  
 ClientType: Environmental Service Firm  
 ProjectNumber: Project #1  
 Substrates: Wood  
 PartType: Coupon  
 Contaminants: Coatings  
 Cleaning Methods:  
 Analytical Methods: Performance Test

Purpose: To evaluate small load impact for additional floor finishes.

Experimental Procedure: The moisture content at the time of testing will influence results due to the hygroscopic nature of the base materials. Therefore, efforts must be taken to ensure that the moisture content and temperature remain constant during the evaluation period. Ideally, the sample floor should be kept at 65+/-1% relative humidity and 68+/-6 F.

During laboratory testing, conditions were slightly drier, 40% relative humidity, but the temperature was within the given temperature range ~70 F).

The flooring material supplied was Hardwood flooring made from Red Oak. The boards were ¾" thick, 2 ¼" wide and cut into 8" sections. Some pieces of the flooring had to be sanded prior to making initial thickness readings to remove residual packing tape adhesive.

According to the ASTM method, coupons will be subjected to the indentation damage from small area loads to obtain a measure of the resistance to sharp-edged small area loadings. Results obtained from this test are qualitative in nature. Relative finish performance will be compared among the various tested products.

Testing deviated from the ASTM method for sample size and test directions. This was due to the quantity of wood coupons that would be needed for testing.

The small area load apparatus was constructed using a wooded rolling pin that was implanted with metal trim nails with a 0.15 inch head. The nails were placed 1" apart along an 8" line. Subsequent lines were off-set by ½" from the previous row of nails. The rows were spaced at ¾" around the rolling pin. See Figure 1 for the small area load apparatus.

Figure 1. Small Load Apparatus

Each coupon was clamped between two boards so that the coupon would be held in place during the small area load testing. The superimposed load was provided by the experimenter pushing with a uniform force onto the rolling pin (unknown level but approximately equal for all products). The small load apparatus was rolled across the surface of the coupon for 100 trips (50 cycles). At the end of the 100 trips, the damage to the coupon was classified according to the ASTM method as having none-minor, moderate, severe and complete damage. In addition, two independent assessments were made by lab personnel to rank the finishes for its ability to withstand small area loading.

Results: Visual analysis made by two observers for the level of damage to the coated wood boards. Rankings were made independent of each other.

Observer 1			Observer 1	Observer 2
Product	Observations	ASTM Classification	Rank	Rank
Hydro 202 Satin	Cut and scraped, breaking through finish	Moderate	3	3
SafeCoat Satin	some damage, chipping	Minor/Moderate	2	2
SafeCoat Gloss	Looked less damaged because of shine	Minor/Moderate	1	1

Summary

## CLEANING LABORATORY EVALUATION SUMMARY

	Overall Ranking
Polyurethane Gloss	7
WB Polyurethane	1
WB Sanding Sealer	6
Aqua Deva Metro	3
Hydro 202 Satin	5
SafeCoat Satin	4
SafeCoat Gloss	2

Summary:

Conclusion:

Both observers scored the SafeCoat Gloss as having had the least amount of damage for the three products tested. The overall results of the seven products yielded the polyurethane from Pro Finishers as the product that had the least amount of damage. The polyurethane from Capitol was the most damaged for both observers.