

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2019  
 DateRun: 10/04/2019  
 Experimenters: Nicole Kebler, Rimsha Paneru  
 ClientType: Electroplating Company  
 ProjectNumber: Project #2  
 Substrates: Graphite  
 PartType: Part  
 Contaminants: Fluxes, Solder  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Visual

Purpose: To evaluate cleaners effectiveness at removing flux on graphite fixtures.

Experimental Procedure: Pre-contaminated graphite fixtures were provided by the company. Each of the four cells on one fixture was rated based on how contaminated they were initially and rated again after drying. The following visual rating keys were used.

## Initial Visual Rating Key

#	Description
1	No contamination
2	Minimal contamination
3	Partially contaminated
4	Mostly contaminated
5	Completely contaminated

## Final Visual Rating Key

#	Description
1	Completely removed
2	Mostly removed
3	Partially removed
4	Minimal removal
5	No removal

One fixture was immersed in an unheated cleaner for 15 minutes. Visual observations of the fixture and flux removal were taken every five minutes, and the fixtures were air dried with room temperature forced air for five minutes before final observations.

Results: Visual Observations:

Cleaner	5 Mins	10 mins	15 mins	Dry
1	- no visible bubbles - clear dilution	- no change	- no change	-Flux still present, minimal removal
2	- no visible bubbles - clear dilution	- no change	- no change	-Little to no removal

## CLEANING LABORATORY EVALUATION SUMMARY

3	- no visible bubbles - clear dilution	- no change	- no change	-No removal
4	- Bubbles on rim	- no change	-no change	-Minimal removal
5	- Bubbles on rim	- no change	- no change	-Little to no removal
6	-No change, No bubbles	- no change	- no change	- Residue left in middle
7	- Bubbles on surface	-Bubbles appearing	-Bubbles disappear	-No removal

Average Ratings:

Cleaner	Average Before Cleaning	Average After Cleaning
1	4.5	4
2	5	4.5
3	4.5	4.5
4	5	4
5	5	4.5
6	5	4.5
7	5	5

Summary:

<b>Substrates:</b>	Graphite				
<b>Contaminants:</b>	Fluxes, Solder				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Fisher Scientific	Isopropanol (CAS: 67-63-0)	99%		<input type="checkbox"/>	
JR Hess & Co., Inc.	Sta-Sol ESS 160	100%		<input type="checkbox"/>	
Alconox Inc	Liquinox	1%		<input type="checkbox"/>	
Brulin Corporation	Aquavantage 1400	5%		<input type="checkbox"/>	
International Products Corporation	Micro 90 Conc.	2%		<input type="checkbox"/>	
Fisher Scientific	Isopropanol (CAS: 67-63-0)	70%		<input type="checkbox"/>	
Fisher Scientific	Isopropanol (CAS: 67-63-0)	10%		<input type="checkbox"/>	

Conclusion:

None of the cleaners were effective with unheated immersion. Next step will be to add heat to cleaners that can be heated safely without engineering controls.