

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2022
 DateRun: 05/24/2022
 Experimenters: Zoe Lawson, Tatyanna Moreland Junior
 ClientType: Brass Instrument Manufacturer
 ProjectNumber: Project #1
 Substrates: Brass
 PartType: Coupon
 Contaminants: Buffing/Polishing Compounds
 Cleaning Methods: Ultrasonics
 Analytical Methods: Gravimetric, Visual

Purpose: To test the effectiveness of cleaners on USP Gk-7 Lap Compound

Experimental Procedure: Three pre-weighed brass coupons per substrate were soiled with USP Gk-7 Lapping Compound using a cotton swab. The soil was allowed to dry for two hours. Both cleaners were then heated to approximately 125F and the coupons were placed in their respective cleaner for 15 minutes in the ultrasonics tank. Following ultrasonics, the coupons were allowed to air dry overnight and the next day the final weights were recorded.

Results: Emerald HD had a high removal yield for all coupons except for one. This error may have been due to the coupon moving and getting stuck to another one, hindering the cleaning process. Shopmaster LPH had one high removal coupon and two others that were less effective.

Cleaner	Initial wt of cont.	Final wt of cont.	%Cont Removed	Average % Removal
Emerald HD	0.3283	0.0031	99.06	92.48
	0.3401	0.0701	79.39	
	0.5706	0.0057	99.00	
Shopmaster LPH	0.4324	0.0022	99.49	90.92
	0.5939	0.0849	85.70	
	0.4693	0.0584	87.56	

Summary:	Substrates:	Brass				
	Contaminants:	Buffing/Polishing Compounds				
	Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
	Hubbard Hall Inc	Emerald HD2	1:16	92.48	<input type="checkbox"/>	
	Buckeye International	Shopmaster LPH	15%	90.92	<input type="checkbox"/>	

Conclusion: Emerald HD and Shopmaster LPH (at a higher concentration) were chosen as aqueous solutions that had not been tested yet to possibly solve S.E. Shires issues with Metalnox. Further testing is needed to determine the overall effectiveness of both and if one could resolve the cloudiness from actual parts.