

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2006
 DateRun: 06/06/2006
 Experimenters: Jason Marshall
 ClientType: General
 ProjectNumber: Project #1
 Substrates: Steel
 PartType: Part
 Contaminants: Paints
 Cleaning Methods:
 Analytical Methods:

Purpose: Summary of testing performed on alternatives for paint removal from steel spindles.

Experimental Procedure: Ten trials were conducted on the various paints used in painting golf balls. During the evaluations, one of the current cleaning chemicals was used as a bench mark. Successful products were identified that could be used to clean the manufacturing equipment, i.e. spindles.

Results: Oakite Products Inproclean 4000 T and International Products Surface Cleanse 930 were effective on the RPM Wood Finishes Group paint combinations. The Inproclean 4000 T was also effective for the Westfield Coatings Company paints and the water based coating as well. However Surface Cleanse 930 did not remove enough of the paint to be considered successful. A third product, Gemtek Products SC Actisol, was tested on the Westfield Coatings Company and the water based coating. This product was effective on the supplied spindles.

Follow up testing on the RPM Wood Finishes Group paints using coupons showed that SC Actisol was very effective in removing the two RPM Wood Finishes Group paints and the Westfield Coatings Company paint.

The table summarizes the testing for the various paint mixtures on the steel based substrates. Products with empty cells were not tested for that paint mixes. The eight paint combinations are described as well.

Table 1. Steel Cleaning Summary

Product	Mix #	1	2	3	4	5	6	7	8
D Solve 1012-current solvent		Yes	Yes	Yes		Yes		Yes	
Solsafe 245		Yes	Yes	Yes	No		No		
Aquavantage 3800 GD		Yes	Yes	Yes					
Shopmaster		No							
Optisol OP7171		No							
Inproclean 4000 T		Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Beyond 2006		Yes	No						
A 2000 XS		Yes	Yes	No	No				
Surface Cleanse 930		Yes	Yes	Yes	Yes	No		No	
SC Aircraft & Metal Cleaner						No			
Citrus Burst 7						Yes	No		
Canola gold CE 110						No			
Shopmaster RC						No			
SC Actisol		Yes	Yes			Yes	Yes	Yes	Yes
DBE 5/6								No	

Table 2. Paint Mix Components

CLEANING LABORATORY EVALUATION SUMMARY

Paint Mix 1	Paint Mix 2	Paint Mix 3	Paint Mix 4	Paint Mix 5	Paint Mix 6	Paint Mix 7	Paint Mix 8
RPM Wood Finishes Group. MS2664 Catalyst White (108-10-1, 28182-81-2, 822-06-0) MS2669 Primer (108-10-1, 28182-81-2, 822-06-0)	RPM Wood Finishes Group MS2664 Catalyst White (108-10-1, 28182-81-2, 822-06-0) 9-6LP9258 White Primer Topcoat (13463-67-7, 110-43-0, 123-86-4, 108-10-1, 108-38-3)	Paint Mix 1 Paint Mix 2	RPM Wood Finishes Group paint mixtures Oil, dirt and grime	Westfield Coatings Company ARC Fast Dry (108-10-1) ARC Fast Dry Catalyst (123-86-4, 110-43-0, 108-65-6)	Paint Mix 5 Oil, dirt and grime	Witcobond W-235 (71173-87-0) Crosslinker (64265-57-2) DI water	Paint Mix 7 Oil, dirt and grime
Ratio 3:1	Ratio 3:1	Ratio 1:1		Ratio: 2:1		Ratio: 40:2:1	

Summary:

Conclusion:

Oakite Inproclean 4000 T and Gemtek SC Actisolv were successful on each of the paints. Both products cleaned the supplied spindles very well when using ultrasonic energy.