

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1997

DateRun: 10/23/1997

Experimenters: Jason Marshall, Prashant Trivedi

ClientType: Manufacturers of Harmonic Drive

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Greases

Cleaning Methods: Low Pressure Spray

Analytical Methods: Visual

Purpose: Evalaute low pressure washer for grease cleaning

Experimental Procedure: The purpose of the experiment was to determine if a low pressure parts washer would be effective in removing the contaminant from the coupons.

Coupons were contaminated in the same way as the previous trials. A Miele low pressure(15psi) parts washer was used in conjunction with cleaning chemistry designed for such a system. The coupons were loaded into the washer in a way to maximize the use of the spraying. To do this, the coupons were clipped upside down to the sides of the pull out tray. The powder cleaner was deposited into the washer. The cleaning, rinsing and drying cycle lasted for about thirty minutes. The operating temperature was between 170 and 180 F.

Company Name Chemistry Name  
Alconox, Inc. Alcojet  
SUBSTRATE MATERIAL: 17-4 Stainless steel  
CONTAMINANTS: Braycote 601-perfluoropolyether grease

Results: The low pressure washing of the coupons were very effective in removing the grease from the stainless steel coupons.

Summary:

<b>Substrates:</b>	Stainless Steel				
<b>Contaminants:</b>	Greases				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Alconox Inc	Alcojet	5		<input checked="" type="checkbox"/>	

Conclusion: Evaluation of three different types of equipment has resulted in the identification of one effective system. Low pressure spray washing removed a majority of the grease.