

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1998  
 DateRun: 09/14/1998  
 Experimenters: Jason Marshall, Shyam Sarda  
 ClientType: Electromagnetic Manufacturer  
 ProjectNumber: Project #1  
 Substrates: Copper, Nickel  
 PartType: Coupon  
 Contaminants: Cutting/Tapping Fluids, Lubricating/Lapping Oils, Oil  
 Cleaning Methods: Ultrasonics  
 Analytical Methods: Gravimetric

Purpose: To determine the minimum cleaning time for the selected aqueous cleaner on second oil

Experimental Procedure: Twelve pre-weighed coupons were contaminated with oil using a hand held swab and then weighed. One cleaning solution was made into 15% solutions using DI water in a 600 mL beaker. The solutions were heated to 130 F on a hot plate. The beakers were then placed into a Crest 40 kHz ultrasonic tank model 4Ht 1014-6 also at 130 F. Three coupons were placed in each cleaner for a set cleaning time. The cleaning time were 30, 60 120, and 180 seconds. Coupons were rinsed in tap water at 120 F for 30 seconds and air dried. Final weights were taken after drying was complete.

SUBSTRATE MATERIAL: Copper/Nickel 70/30

CONTAMINANTS: Oil- Indopol L-14 (Polybutene/butene copolymer CAS# 9003-29-6)

Results: Calgon AK 6215 worked exceptionally well during all of the cleaning times. Table 1 lists the cleaning results from this trial.

Table 1. Cleaning Efficiency of Calgon Ak-6215

Cleaning Time (sec)	30	60	120	180
Coupon 1	102.1	100.6	100.4	99.4
Coupon 2	101.1	100.5	99.8	99.9
Coupon 3	101.0	99.1	100.0	100.1
Ave	101.4	100.1	100.1	99.8
Std Dev	0.6	0.8	0.3	0.4

Summary:

<b>Substrates:</b>	Copper, Nickel				
<b>Contaminants:</b>	Cutting/Tapping Fluids, Lubricating/Lapping Oils, Oil				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Calgon Corporation	AK 6215	15	100.07	<input checked="" type="checkbox"/>	

Conclusion: The Calgon product has been determined to clean both contaminants in under 1 minute.