

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999  
 DateRun: 04/29/1999  
 Experimenters: Jason Marshall  
 ClientType: Electron & Ion Technology Co  
 ProjectNumber: Project #1  
 Substrates: Alloys  
 PartType: Coupon  
 Contaminants: Cutting/Tapping Fluids, Lubricating/Lapping Oils, Dirt, Oil  
 Cleaning Methods:  
 Analytical Methods: OSEE  
 Purpose: To determine if the brown gunk contaminant would change the OSEE readings differently than the metal working fluid.  
 Experimental Procedure: OSEE readings were taken from a clean coupon. The metal working fluid was centrifuged for five minutes at about 1000 rpm using a Fisher Scientific Centrifuge Model 225. A plastic eye dropper was immersed to the bottom of the test tube and the metal working fluid was withdrawn. The metal working fluid was then placed on the coupon (upper section) and wiped with a handheld swab. OSEE readings of the coupon and metal working fluid were recorded. A second eye dropper was used to withdraw the brown gunk from the top of the test tube and placed on the coupon (lower section) and wiped with a new handheld swab. OSEE readings were measured for the coupon and brown gunk.  
 SUBSTRATE MATERIAL: Molybdenum coupon  
 CONTAMINANTS: Metal working fluid (Hangsterfer's S-500CF\_US) & Brown gunk  
 CONTAMINATING PROCESS USED: After initial OSSE readings, parts contaminant was wiped on using swab.  
 Results: Both contaminant OSEE readings were found to decrease from the original clean coupon values. The brown gunk lowered the readings less than the metal working fluid. Table 1 lists the readings obtained for each contaminant and the averages and standard deviations.

|         | Clean Readings | Metal Working fluid | Brown Contaminant |
|---------|----------------|---------------------|-------------------|
|         | 203            | 169                 | 184               |
|         | 220            | 173                 | 197               |
|         | 230            | 176                 | 201               |
|         | 232            | 184                 | 205               |
|         | 222            | 162                 | 186               |
|         | 211            | 194                 | 200               |
| Average | 220            | 176                 | 196               |
| Std Dev | 11.1           | 11.3                | 8.55              |

Although the readings for the brown contaminant were shown to affect the OSEE readings differently than the metal working fluid, the contaminant did not cause the readings to become higher than the original clean coupon.

Summary:

Conclusion: Despite determining that the second contaminant (brown gunk) affected OSEE readings differently than the metal working fluid, the values were not higher than the base line readings. Further examination of OSEE readings needs to be performed on the original parts using the same procedure as in the first experiment conducted for the client.