CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999

DateRun: 07/11/1999

Experimenters: Nicole Vayo

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Oil

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Six products were diluted to 5% and heated to 122 F. Stainless steel coupons were coated with an oil (64741-89-5)

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Alconox Inc	Det-O-Jet	5	100.00	☑	
Baum's Castorine Company Inc	EZE Oil-Grease Cleaner	5	101.00	☑	
Baum's Castorine Company Inc	Protecto Clean 148	5	102.00	☐	
EcoLink	Safe Strip	5	101.00	☑	
Master Chemical Corporation	Trim Rinse 200	5	101.00	☑	
OCS System	# NFH2002	5	98.00	☑	

Conclusion: All six appeared to remove over 98%. Will check to ensure no substrate damage occurring.