

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2006
DateRun: 11/07/2006
Experimenters: Jason Marshall, Heidi Wilcox
ClientType: Metal Finishing
ProjectNumber: Project #1
Substrates: Plastic
PartType: Part
Contaminants: Buffing/Polishing Compounds
Cleaning Methods: Immersion/Soak
Analytical Methods: Visual

Purpose: To evaluate selected cleaners on supplied parts using immersion cleaning followed by spray cleaning.

Experimental Procedure: Two cleaning products were diluted to 5% using hot tap water (130 F) in 1000 ml beakers. Supplied parts that were received already contaminated were cleaned in the immersion solution for two minutes and then cleaned in the spray system for one minute. Two types of parts were cleaned in each solution. Following cleaning in the low-pressure spray system parts were rinsed for 15 seconds in a tap water bath at 120 F and dried using dry compressed air at room temperature. Parts were analyzed visually. Cleaned parts were packaged and sent to the client.

Results:	Cleaner	Part	Observation
	Polyspray Jet	Angel with harp	Removal of contaminant evident in cleaning solution
		Santa Clause	
	Detergent 8	Angel with harp	Removal of contaminant evident in cleaning solution
		Mrs. Clause	

Summary:	Substrates:		Plastic			
	Contaminants:		Buffing/Polishing Compounds			
	Company Name:		Product Name:	Conc.:	Efficiency:	Effective:
	US Polychem Corporation		Polyspray Jet 790 XS	5		<input checked="" type="checkbox"/>
	Alconox Inc		Detergent 8	5		<input checked="" type="checkbox"/>

Conclusion: Both solutions at the lower concentration appeared to remove the buffing compound using 2 minutes of immersion and 1 minute of spray cleaning. Parts have been sent back for client inspection.