

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2006
 DateRun: 11/20/2006
 Experimenters: Jason Marshall
 ClientType: Metal Finishing
 ProjectNumber: Project #1
 Substrates: Aluminum, Plastic
 PartType: Part
 Contaminants: Buffing/Polishing Compounds
 Cleaning Methods: Low Pressure Spray
 Analytical Methods: Visual

Purpose: To evaluate selected cleaners on supplied parts using immersion cleaning followed by spray cleaning.

Experimental Procedure: Two cleaning products were diluted to 5% and 2.5% using room temperature tap water (68 F) in 1000 ml beakers. Supplied parts that were received already contaminated were cleaned in the immersion solution for one minute and then cleaned in the spray system for one minute. One part was cleaned in each solution. Following cleaning in the low-pressure spray system parts were rinsed for 15 seconds in a tap water spray at 68 F and dried using dry compressed air at room temperature. Parts were analyzed visually. Cleaned parts were packaged and sent to the client.

Results: Both products removed the buffing compound at the higher concentration (5%). The Detergent 8 appeared to work at the lower concentration (2.5%) as well.

Cleaner	Concentration	Observation
Detergent 8	5	Part looked clean. The cleaning solution appeared dirty after cleaning.
Jet 790 XS	5	Part not as clean as Det 8 @ 5%.
Detergent 8	2.5	Part not as clean as Det 8 @ 5% but as clean as Jet 790 XS @ 5.0%
Jet 790 XS	2.5	Water retention inside small opening, required slightly longer drying time to remove.

Summary:

Substrates:	Aluminum, Plastic				
Contaminants:	Buffing/Polishing Compounds				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Alconox Inc	Detergent 8	5		<input checked="" type="checkbox"/>	
US Polychem Corporation	Polyspray Jet 790 XS	5		<input checked="" type="checkbox"/>	
Alconox Inc	Detergent 8	2.5		<input checked="" type="checkbox"/>	
US Polychem Corporation	Polyspray Jet 790 XS	2.5		<input type="checkbox"/>	

Conclusion: Both solutions at the lower concentration appeared to remove the buffing compound using 1 minute of immersion and 1 minute of spray cleaning. Parts have been sent back for client inspection.