

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2006  
 DateRun: 12/10/2006  
 Experimenters: Jason Marshall  
 ClientType: Metal Working  
 ProjectNumber: Project #1  
 Substrates: Brass  
 PartType: Part  
 Contaminants: Buffing/Polishing Compounds  
 Cleaning Methods: Ultrasonics  
 Analytical Methods: Visual

Purpose: To evaluate a client requested product for cleaning buffing compounds from their brass parts.

Experimental Procedure: One product was diluted to two concentrations, 5 and 10% using DI water in 250 ml beakers. Solutions were immersed in a water bath heated to 130 F and degassed using a Branson 3510 ultrasonic tank for five minutes. Six parts were immersed in each solution and cleaned with 40 kHz ultrasonic energy. Parts were rinsed in a tap water spray for 15 seconds at 120 F and dried using room temperature air for 30 seconds. Visual observations were made for both sets of cleaned parts and compared to each other.

Concentration	Observation
5%	The buckles looked very clean
	The stripes also looked very clean
	One of the bars still had some buffing compound remaining.
10%	The buckles looked very clean
	The stripes also looked very clean
	One of the bars still had some buffing compound remaining - less than the 5%

<b>Substrates:</b>		Brass			
<b>Contaminants:</b>		Buffing/Polishing Compounds			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Hubbard Hall Inc	Ultrasoak 127	5	0.00	<input checked="" type="checkbox"/>	
Hubbard Hall Inc	Ultrasoak 127	10	0.00	<input checked="" type="checkbox"/>	

Conclusion: The Hubbard Hall Ultrasoak 127 was very effective on most of the part types cleaned. Both the 5 and 10% dilutions had some trouble removing all the buffing compound from the back of the double bars.