

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999
 DateRun: 07/15/1999
 Experimenters: Nicole Vayo
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Brass
 PartType: Coupon
 Contaminants: Greases, Lubricating/Lapping Oils, Oil
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: One product was diluted to 5% and heated to 130 F. Brass coupons were coated with oil (64741-89-5), lubricant (64742-47-8, 9003-29-6) and a grease (64742-47-8).
 Results: Works very well. Should be included in client testing.

Summary:

| | | | | | |
|----------------------|--|---------------|--------------------|-------------------------------------|----------------------|
| Substrates: | Brass | | | | |
| Contaminants: | Greases, Lubricating/Lapping Oils, Oil | | | | |
| Company Name: | Product Name: | Conc.: | Efficiency: | Effective: | Observations: |
| Jet Lube Inc | Jet Lube 5000 | 5 | 95.00 | <input checked="" type="checkbox"/> | oil |
| Jet Lube Inc | Jet Lube 5000 | 5 | 100.00 | <input checked="" type="checkbox"/> | lubricant |
| Jet Lube Inc | Jet Lube 5000 | 5 | 100.00 | <input checked="" type="checkbox"/> | grease |

Conclusion: The product was successful on all three contaminants.