

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999
 DateRun: 08/17/1999
 Experimenters: Nicole Vayo
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum, Glass/Quartz, Stainless Steel, Steel
 PartType: Coupon
 Contaminants: Coatings, Fluxes, Greases, Lubricating/Lapping Oils
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Coating, CAS: 64742-47-8, 64742-52-5
 Flux, RMA
 Grease, CAS: 64742-47-8
 Lubricant, CAS: 64742-47-8, 9003-29-6

Results:

Summary:

| | | | | | |
|----------------------|---|---------------|--------------------|-------------------------------------|----------------------|
| Substrates: | Aluminum, Glass/Quartz, Stainless Steel, Steel | | | | |
| Contaminants: | Coatings, Fluxes, Greases, Lubricating/Lapping Oils | | | | |
| Company Name: | Product Name: | Conc.: | Efficiency: | Effective: | Observations: |
| Safe Science Inc | Safe Science Engine Degreaser (Industrial) | 100 | 37.40 | <input type="checkbox"/> | coating |
| Safe Science Inc | Safe Science Engine Degreaser (Industrial) | 100 | 99.90 | <input checked="" type="checkbox"/> | flux |
| Safe Science Inc | Safe Science Engine Degreaser (Industrial) | 100 | 99.50 | <input checked="" type="checkbox"/> | grease |
| Safe Science Inc | Safe Science Engine Degreaser (Industrial) | 100 | 100.00 | <input checked="" type="checkbox"/> | lubricant |

Conclusion: