CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	1999
DateRun:	12/07/1999
Experimenters:	Nicole Vayo
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Brass, Ceramics, Copper, Nickel
PartType:	Coupon
Contaminants:	Coatings, Greases, Inks, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Coating, CAS: 64742-47-8, 64742-52-5 Grease, CAS: 64742-47-8 Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5
Results:	
Summary:	

Substrates:	Aluminum, Brass, Ceramics, Copper, Nickel				
Contaminants:	Coatings, Greases, Inks, Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
CRC Industries	Complex Blue	5	84.60	☑	coating
Oakite Products	Fisan Versaclean	5	98.50	☑	grease
Quaker Chemical	Formula 625 XL	5	36.00	☐	ink
Oakite Products	Fisan Versaclean	5	12.20	☐	ink
Quaker Chemical	Formula 625 XL	5	98.90	☑	coating
Quaker Chemical	Formula 625 XL	5	10.20	☐	ink

Conclusion: