CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	1999
DateRun:	12/06/1999
Experimenters:	Nicole Vayo
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Brass, Stainless Steel, Steel
PartType:	Part
Contaminants:	Greases, Lubricating/Lapping Oils, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant:Grease, CAS: 64742-47-8 Lubricant, CAS: 8052-42-4, 64742-57-0, 64742-62-7 Oil, CAS: 64741-89-5, 64742-53-6, 64741-44-2
Results:	
Summary:	

Substrates:	Aluminum, Brass, Stainless Steel, Steel				
Contaminants:	Greases, Lubricating/Lapping Oils, Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
United Laboratories International	United 2002 Harvest Gold	100	65.90	☐	lubricant
United Laboratories International	United 2002 Harvest Gold	100	-12.00	☐	oil
United Laboratories International	United 2002 Harvest Gold	100	64.90	☐	
United Laboratories International	United 450 All Clear	5	94.40	☑	lubricant
United Laboratories International	United 450 All Clear	5	90.70	☑	oil
United Laboratories International	United 450 All Clear	5	99.85	☑	grease

Conclusion: