CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2000
DateRun:	01/02/2000
Experimenters:	Nicole Vayo
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Brass, Copper, Nickel, Stainless Steel
PartType:	Coupon
Contaminants:	Greases, Lubricating/Lapping Oils, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Oil, CAS: 64741-89-5, 8052-42-4 Lubricant, CAS: 8052-42-4, 64742-57-0, 64742-62-7 Grease, CAS: 64742-47-8
Results:	
Summary:	

Substrates:	Aluminum, Brass, Copper, Nickel, Stainless Steel				
Contaminants:	Greases, Lubricating/Lapping Oils, Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
EnviroSan Products Ltd	Solution 2000	5	96.00	☑	oil
EnviroSan Products Ltd	Solution 2000	5	43.20	☐	lubricant
EnviroSan Products Ltd	Solution 2000	5	95.70	☑	grease
JDI Inc	Mirachem 500 RTU	5	75.90	☐	lubricant
JDI Inc	Mirachem 500 RTU	5	94.00	☑	grease
JDI Inc	Mirachem 500 RTU	5	98.70	☑	oil
Mirachem Corporation	Mirachem 500	5	92.00	☑	oil
Mirachem Corporation	Mirachem 500	5	91.30	☑	lubricant
Mirachem Corporation	Mirachem 500	5	98.60	☑	lubricant

Conclusion: