

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 03/31/2001  
 Experimenters: John Brunelle  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Aluminum, Brass, Copper, Glass/Quartz, Nickel, Stainless Steel  
 PartType: Coupon  
 Contaminants: Coatings, Greases, Inks, Oil  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5  
 Grease, CAS: 64742-47-8  
 Oil, CAS: 64741-89-5, 8052-42-4  
 Coating, CAS: 64742-47-8, 64742-52-5

## Results:

### Summary:

<b>Substrates:</b>	Aluminum, Brass, Copper, Glass/Quartz, Nickel, Stainless Steel				
<b>Contaminants:</b>	Coatings, Greases, Inks, Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Pride International Inc	Citrisolv Plus	10	-30.40	<input type="checkbox"/>	ink
Pride International Inc	Citrisolv Plus	10	72.40	<input type="checkbox"/>	coating
Kyzen Corporation	Ionox FCR (For Comparison Only)	100	98.16	<input checked="" type="checkbox"/>	grease
Kyzen Corporation	Ionox FCR (For Comparison Only)	100	94.20	<input checked="" type="checkbox"/>	oil
Kyzen Corporation	Ionox FCR (For Comparison Only)	100	53.73	<input type="checkbox"/>	coating
Finger Lakes Chemical	FLSC-12 Resineater Sample	100	87.57	<input checked="" type="checkbox"/>	ink
Finger Lakes Chemical	FLSC-12 Resineater Sample	100	87.23	<input checked="" type="checkbox"/>	grease
Finger Lakes Chemical	FLSC-12 Resineater Sample	100	85.73	<input checked="" type="checkbox"/>	oil
EcoLink	Safe Strip	100	71.61	<input type="checkbox"/>	ink
EcoLink	Safe Strip	100	70.82	<input type="checkbox"/>	grease

### Conclusion: