CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2000
DateRun:	03/30/2000
Experimenters:	John Brunelle
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Brass, Copper, Nickel, Plastic, Stainless Steel
PartType:	Coupon
Contaminants:	Adhesive, Greases, Inks, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5 Oil, CAS: 64741-89-5, 8052-42-4 Grease, CAS: 64742-47-8 Adhesive. Acylic Sealer 5504
Results:	

Summary:

Substrates:	Aluminum, Brass, Copper, Nickel, Plastic, Stainless Steel				
Contaminants:	Adhesive, Greases, Inks, Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Loctite Corporation	7360	100	-127.30	☐	ink
Loctite Corporation	7360	100	-87.63	☐	grease
Inland Technologies Inc	Citrasafe	100	46.46	☐	ink
Inland Technologies Inc	Citrasafe	100	96.30	☑	grease
Inland Technologies Inc	Citrasafe	100	102.90	☐	oil
Inland Technologies Inc	Citrasafe	100	0.60	☑	adhesive

Conclusion: