CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2000
DateRun:	03/20/2000
Experimenters:	Nicole Vayo
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Aluminum, Brass, Ceramics, Stainless Steel
PartType:	Coupon
Contaminants:	Greases, Inks, Lubricating/Lapping Oils, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Grease, CAS: 64742-47-8 Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5 Lubricant, CAS: 8052-42-4, 64742-57-0, 64742-62-7 Oil, CAS: 64741-89-5, 8052-42-4
Results:	
Summary:	

Substrates:	Aluminum, Brass, Ceramics, Stainless Steel				
Contaminants:	Greases, Inks, Lubricating/Lapping Oils, Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Drummond America Corporation	Keynote	100	99.34	☑	grease
Drummond America Corporation	Keynote	100	7.40	☐	ink
Drummond America Corporation	Keynote	100	99.55	☑	lubricant
Drummond America Corporation	Keynote	100	99.80	☑	oil
Drummond America Corporation	Clout	5	98.88	☑	grease
Drummond America Corporation	Clout	5	8.62	☐	ink
Drummond America Corporation	Clout	5	99.66	☑	lubricant
Drummond America Corporation	Clout	5	96.53	☑	oil

Conclusion: