

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 07/05/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Adhesive
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Adhesive Ashland Aroset 8034, CAS: 141-78-6, 67-63-0, 108-88-3

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Adhesive				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Savogran Company	SI #4 Coating Remover	100	2.66	<input type="checkbox"/>	
Buckeye International	Shopmaster	20	5.41	<input type="checkbox"/>	
Dysol	DS 104 Wipe Solvent	100	8.20	<input type="checkbox"/>	
Bio Chem Systems	Bio T 200 A	100	0.57	<input type="checkbox"/>	
Bio Chem Systems	Bio T Max	100	-4.92	<input type="checkbox"/>	
Inland Technologies Inc	EP 921	100	-8.70	<input type="checkbox"/>	
Safe Science Inc	Safe Science Engine Degreaser (Industrial)	100	7.40	<input type="checkbox"/>	
Transene Company, Inc.	D Greeze 500 LO	100	4.20	<input type="checkbox"/>	
Twin Rivers Technologies	Methyl Ester 1618	100	-85.60	<input type="checkbox"/>	

Conclusion: