CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2001
DateRun:	07/09/2001
Experimenters:	Ravi Krishnappa
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Stainless Steel
PartType:	Coupon
Contaminants:	Inks, Oil
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evaluation. Contaminant: Ink, Tough Tex Oil, Hydraulic, CAS: 64742-65-0
Results:	
Summary:	

Substrates:	Stainless Steel				
Contaminants:	Inks, Oil				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Heatbath Corporation	Uni Kleen 10	4	4.75	☐	ink
Heatbath Corporation	Uni Kleen 10	4	78.00	☐	oil
International Bio System	Bio Z	10	-0.19	☐	ink
International Bio System	Bio Z	10	94.80	☑	oil
MacDermid Industrial Products	New Dimensions LF Supreme	4	-0.74	☐	ink
MacDermid Industrial Products	New Dimensions LF Supreme	4	63.20	☐	oil

Conclusion: