

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 07/10/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Inks, Oil
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Ink, Tough Tex
 Oil, Hydraulic, CAS: 64742-65-0

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Inks, Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Heatbath Corporation	Uni Kleen 10	4	4.75	<input type="checkbox"/>	ink
Heatbath Corporation	Uni Kleen 10	4	78.00	<input type="checkbox"/>	oil
International Bio System	Bio Z	10	-0.19	<input type="checkbox"/>	ink
International Bio System	Bio Z	10	94.80	<input checked="" type="checkbox"/>	oil
MacDermid Industrial Products	New Dimensions LF Supreme	4	-0.74	<input type="checkbox"/>	ink
MacDermid Industrial Products	New Dimensions LF Supreme	4	63.20	<input type="checkbox"/>	oil

Conclusion: