

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 07/17/2001  
 Experimenters: Ravi Krishnappa  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Adhesive  
 Cleaning Methods: Ultrasonics  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Adhesive Ashland Aroset 8034, CAS: 141-78-6, 67-63-0, 108-88-3

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel			
<b>Contaminants:</b>		Adhesive			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Loctite Corporation	7360	100	-6.40	<input type="checkbox"/>	
Dysol	DS 104 Wipe Solvent	100	14.00	<input type="checkbox"/>	
AW Chesterton	KPC 820 N	20	12.20	<input type="checkbox"/>	

### Conclusion: