

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 07/18/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Coatings

Cleaning Methods: Ultrasonics

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Coating, Heraeus Covercoat L406, CAS: 85-68-7, 108-67-8

Results:

Summary:

Substrates:		Stainless Steel			
Contaminants:		Coatings			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
International Bio System	Bio Z	10	41.30	<input type="checkbox"/>	
Heatbath Corporation	Uni Kleen 10	4	40.60	<input type="checkbox"/>	
Heatbath Corporation	MultiKleen LX 1573	5	38.60	<input type="checkbox"/>	
Innovative Organics Inc	Amberclean SC 11	5	41.70	<input type="checkbox"/>	
MacDermid Industrial Products	New Dimensions LF Supreme	4	40.90	<input type="checkbox"/>	

Conclusion: