CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 07/23/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Lubricating/Lapping Oils

Cleaning Methods: Immersion/Soak

Analytical Methods:

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Lubricant, Keystone Nevastone 6, CAS: 64742-47-8, 8042-47-5, 9003-29-6

Results:

Summary:

Substrates:	Aluminum				
Contaminants:	Lubricating/Lapping Oils				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Transene Company, Inc.	D Greeze 500 LO	100	98.40	☑	
Inland Technologies Inc	EP 921	100	98.80	☑	
Buckeye International	Shopmaster	20	91.02	☑	
Safe Science Inc	Safe Science Engine Degreaser (Industrial)	100	101.00	☑	

Conclusion: