CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 08/08/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Steel

PartType: Coupon

Contaminants: Waxes

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Paraffin Wax

Results:

Summary:

Substrates:	Steel				
Contaminants:	Waxes				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Emkay Chemical Company	Safety Wash	25	-0.81	☐	
Emkay Chemical Company	Safety Wash CRC	25	-0.56	☐	
Emkay Chemical Company	Safety Wash Clear	25	-0.62	☐	
US Polychem Corporation	87 RB	100	64.00	☐	
Gemtek Products	SC 1000 Aqueous Cleaner Concentrate	25	-1.03	☐	
Alconox Inc	Citranox	3	0.19	☐	

Conclusion: