

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 08/16/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum
 PartType: Coupon
 Contaminants: Coatings
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Coating, Ferrocoate 5815, CAS: 64742-47-8, 64742-52-5

Results:

Summary:

Substrates:	Aluminum				
Contaminants:	Coatings				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Alconox Inc	Citranox	3	48.70	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash	25	56.70	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash CRC	25	65.60	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash Clear	25	60.50	<input type="checkbox"/>	
Savogran Company	SI #4 Coating Remover	100	79.20	<input type="checkbox"/>	
Twin Rivers Technologies	Methyl Ester 1618	100	83.60	<input checked="" type="checkbox"/>	

Conclusion: