

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 08/24/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Coatings

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Laboratory evaluation.  
Contaminant: Coating, Ferrocote 5815, CAS: 64742-47-8, 64742-52-5

## Results:

### Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Coatings				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
US Polychem Corporation	87 RB	100	99.90	<input checked="" type="checkbox"/>	
AG Environmental Products	Soy Gold 2000	25	83.50	<input checked="" type="checkbox"/>	
Inland Technologies Inc	EP 921	100	85.80	<input checked="" type="checkbox"/>	

### Conclusion: