

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 08/30/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Paints

Cleaning Methods: Ultrasonics

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Paint, Painter Touch Blue, CAS: 67-64-0, 1330-20-07

Results:

Summary:

Substrates:		Aluminum			
Contaminants:		Paints			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Invista S.a.r.l	Flexisolv DBE 4 ester	100	103.50	<input type="checkbox"/>	
Twin Rivers Technologies	Methyl Ester 1618	100	86.70	<input checked="" type="checkbox"/>	

Conclusion: