

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 08/31/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Inks

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Laboratory evaluation.  
Contaminant: Ink, Cerdec Magenta, CAS: 65947-18-4, 1345-24-0, 20667-12-3

## Results:

### Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Inks				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Savogran Company	HD-34 Cleaner Degreaser	50	13.50	<input type="checkbox"/>	
AG Environmental Products	Soy Gold 2000	25	1.57	<input type="checkbox"/>	
US Polychem Corporation	87 RB	100	23.72	<input type="checkbox"/>	
Savogran Company	SI #4 Coating Remover	100	22.22	<input type="checkbox"/>	
Gemtek Products	SC 1000 Aqueous Cleaner Concentrate	25	18.01	<input type="checkbox"/>	
Loctite Corporation	7360	100	91.66	<input checked="" type="checkbox"/>	
Transene Company, Inc.	D Greeze 500 LO	100	62.30	<input type="checkbox"/>	
Gemtek Products	SC Supersolve Safety Solvent	30	14.21	<input type="checkbox"/>	

### Conclusion: