

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 10/02/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Adhesive

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Adhesive Ashland Acrylic Sealant 5504, CAS: 108-88-3, 141-78-6, 142-82-5, 67-63-0

Results:

Summary:

Substrates:		Stainless Steel			
Contaminants:		Adhesive			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Brulin Corporation	Compliance	10	-11.10	<input type="checkbox"/>	
Buckeye International	Shopmaster	5	-12.10	<input type="checkbox"/>	
Mirachem Corporation	Mirachem 500	10	-5.10	<input type="checkbox"/>	
Oakite Products	Inproclean 1300	10	-5.00	<input type="checkbox"/>	
Sky Products Company Inc	Cleaner #10	10	-18.00	<input type="checkbox"/>	
Simple Green	Simple Green D	10	-9.70	<input type="checkbox"/>	
By Pas and Star Products	Star Cleaning Miracle # 50	10	-8.20	<input type="checkbox"/>	
Magnaflux	Daraclean 283	10	-17.50	<input type="checkbox"/>	

Conclusion: