CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 10/11/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Buffing/Polishing Compounds

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Buffing compound, Learok 2 B 111, CAS: 14808-60-7

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Buffing/Polishing Compounds				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Bio Chem Systems	Bio T Max	100	89.40	☑	
Bio Chem Systems	Bio T 300 B	5	2.41	☐	
Warren Chemical Company	Sea Wash 8	5	46.30	☐	
Oakite Products	Inproclean 1300	10	50.40	☐	
By Pas and Star Products	Star Cleaning Miracle # 50	10	-7.50	☐	
US Polychem Corporation	87 RB	100	82.20	☐	
Transene Company, Inc.	D Greeze 500 LO	100	75.40	☐	

Conclusion: