CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 11/28/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Adhesive

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.

i) 5 minute immersion cleaning with stir bar agitation @ 120 degree F.
(ii) 30 sec manual rinse with water @120 degree F.
(iii) air drying for about 24 hours.
CONTAMINANT INFO: Adhesive -Morstik 717- Rohm and Haas
CAS Numbers: 108-88-3, 110-54-3, 142-82-5, 67-63-0, 108-05-4

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Adhesive				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
EnviroSan Products Ltd	Solution 2000	10	7.10	☐	
LPS Laboratories	Precision Clean Concentrate	10	14.60	☐	
EcoLink	Heavy Weight Non Butyl Detergent	10	10.20	☐	
Cleaning Systems	Release	10	13.40	☐	
Ardrox Inc	6333	25	13.40	☐	
Baum's Castorine Company Inc	EZE Oil-Grease Cleaner	25	18.50	☐	

Conclusion: