

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 12/13/2001
 Experimenters: Purav Dave
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Brass
 PartType: Coupon
 Contaminants: Buffing/Polishing Compounds
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min. immersion cleaning at 120 F
 Rinsing: 1/2 min. manual water rinse at 120 F
 Drying: 1 min drying with heat gun at 500 F.
 Contaminant : The Lea manufacturing company- Learock 2-B-111
 Abrasive , fatty acids, glycerides and petroleum wax

Results:

Summary:

Substrates:		Brass			
Contaminants:		Buffing/Polishing Compounds			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Alconox Inc	Alcojet	1	79.31	<input type="checkbox"/>	
Buckeye International	Shopmaster FF	5	165.08	<input type="checkbox"/>	
Buckeye International	Shopmaster HP	5	67.64	<input type="checkbox"/>	
Buckeye International	Shopmaster LPH	5	88.94	<input checked="" type="checkbox"/>	
Calgon Corporation	SC 431	5	82.51	<input type="checkbox"/>	
Buckeye International	Immersion Cleaner	5	96.99	<input checked="" type="checkbox"/>	
Brulin Corporation	Aquavantage 1400	5	106.10	<input type="checkbox"/>	

Conclusion: