CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2002
DateRun:	01/08/2002
Experimenters:	Heidi Wilcox
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Stainless Steel
PartType:	Coupon
Contaminants:	Greases
Cleaning Methods:	Immersion/Soak
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F Rinsing: 1/2 min, manual, in 102 F water (tap) Drying : 1 min with heat gun @ 500F Contaminant : Elf Lubricants, Keystone KSL 111 Synthetic Tacky Grease (spray)
Results:	

Summary:

Substrates:	Stainless Steel				
Contaminants:	Greases				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Kleer Flo Company	Grease Off 2	5	97.38	☑	
Valtech Corporation	Valtron SP 2201	2	91.95	☑	
Valtech Corporation	Valtron SP 2200	2	92.04	☑	
Permatex Industrial Corporation	Natural Blue	5	91.84	☑	
International Products Corporation	LF 2100 (Liquid Foam Cleaner)	5	87.55	☑	
US Polychem Corporation	Polychem PW 147	5	79.57	☐	This cleaner was not effective on the Tacky Spray Grease

Conclusion: All Cleaners were effective except U.S. Polychem PW-147 cleaner (79.57 average % removal)