

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002
 DateRun: 03/15/2002
 Experimenters: Purav Dave
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Latex binder
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min. immersion cleaning at 120 F with stir-bar agitation.
 Rinsing: 1/2 min. manual with water at 120 F
 Drying: 1 min. with heat gun at 500 F
 Contaminant: Latex Binder Mix
 Cas #: 9016-45-9, 79-06-1, 7664-41-7, 924-42-5, 50-00-0, 1333-86-4, 57-55-6, 7732-18-5
 flooroacrylate copolymer emulsion, Linear alkyl benzene sulphonate

Results: Observation:
 1. Cleaning Latex Binder with DS-108-Solvent big pieces of binder were removed as compared to the other cleaners and the solvent remained on the coupons even after rinsing which led to the increase in the weight.
 2. There was no removal of binder by Tarksol HTF-60. Instead, there were pockets formed which retained the cleaner which led to tremendous increase in weight.

Summary:

Substrates:	Stainless Steel				
Contaminants:	Latex binder				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Chemical Technologies	Green Thunder	5	80.59	<input type="checkbox"/>	
CRC Industries	Complex Blue	5	65.29	<input type="checkbox"/>	
United Laboratories International	United 450 All Clear	5	95.06	<input checked="" type="checkbox"/>	
AJ Associates	Dynadet	100	-46.17	<input type="checkbox"/>	
Tarksol Inc	Tarksol HTF 60	100	-509.24	<input type="checkbox"/>	
EnviroSan Products Ltd	Solution 2000	5	70.13	<input type="checkbox"/>	
Heatbath Corporation	Alu-Kleen 36	5	69.28	<input type="checkbox"/>	

Conclusion: Only United 450 all clear was effective.