

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002

DateRun: 05/10/2002

Experimenters: Purav Dave

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Mold Releases

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min. immersion cleaning at 120 F with stir-bar agitation.  
Rinsing: 5 min. manual with water at 120 F  
Drying: 1 min. with heat gun at 500 F.  
Contaminant: GE SM-2163  
Silicone Emulsion  
CAS# 112945-52-5

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel				
<b>Contaminants:</b>		Mold Releases				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>	
Kyzen Corporation	Ionox HC 2	100	97.89	<input checked="" type="checkbox"/>		
Safe Science Inc	Heavy Duty Kitchen Cleaner F1	5	95.06	<input checked="" type="checkbox"/>		
Safe Science Inc	Heavy Duty Kitchen Cleaner F2	5	82.97	<input type="checkbox"/>		
Dow Chemical Company	XUS 40570 Development Solvent	100	96.96	<input checked="" type="checkbox"/>		
Dow Chemical Company	XUS 40579 Development Solvent	100	83.03	<input type="checkbox"/>		
Oakite Products	Inproclean 61 B		99.40	<input checked="" type="checkbox"/>	concentration: 20 g/l	
Oakite Products	Inproclean 2300		97.77	<input type="checkbox"/>	Concentration: 20 g/l	
Magnaflux	Daraclean 121	5	97.60	<input checked="" type="checkbox"/>		
Sysco Corporation	Heavy Duty Kitchen Cleaner	5	90.03	<input checked="" type="checkbox"/>		

### Conclusion: