

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002

DateRun: 12/05/2002

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Fluxes

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F
Rinsing: 1/2 min, manual, in 120 F water (tap)
Drying: 1 min with heat gun @ 500F
Contaminant: VOC Free No Clean Flux, CAS# 7732-18-5, 68937-72-4

Results:

Summary:

Substrates:		Stainless Steel			
Contaminants:		Fluxes			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Buckeye International	XL 100 Cleaner & Degreaser	5	24.42	<input type="checkbox"/>	
Buckeye International	Immersion Cleaner	5	82.36	<input type="checkbox"/>	Vary time, concentration or mechanical energy of cleaning or rinsing to increase efficiency.
Buckeye International	Ambush	5	39.08	<input type="checkbox"/>	
SOQ Environmental Technology	Ecomate FN	5	48.59	<input type="checkbox"/>	
Simple Green	Concentrated Industrial Strength Cleaner and Degreaser	5	11.10	<input type="checkbox"/>	
Magnaflux	Daraclean 236	5	32.85	<input type="checkbox"/>	
Magnaflux	Daraclean 203	5	99.70	<input checked="" type="checkbox"/>	
A 1 Hydro Parke Hill Chemical	SW Wash 10 Aircraft Cleaner	5	37.05	<input type="checkbox"/>	

Conclusion: