

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004
 DateRun: 05/28/2004
 Experimenters: Jason Marshall
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum
 PartType: Coupon
 Contaminants: Oil
 Cleaning Methods: Vapor Degreasing
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Two hundred fifty milliliters of each product were used at full strength in a 4000 ml beaker and heated to its boiling point on a hot plate. Preweighed aluminum coupons were coated with the Nisseki SAS 40 oil (27776-01-8, 612-00-0, 103-29-7, 101-81-5) using a handheld swab. Coupons were weighed a second time to determine the amount of soil added to each coupon. Three coupons were cleaned in each solution for 5 minutes using vapor degreasing. After cooling to room temperature, the coupons were weighed a final time and efficiencies were calculated.

Results:

Summary:

Substrates:		Aluminum				
Contaminants:		Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	
AGA Chemical	AK 225	100	99.64	<input checked="" type="checkbox"/>		
DuPont	Vertrel CCA	100	98.70	<input checked="" type="checkbox"/>		
DuPont	Vertrel MCA	100	99.32	<input checked="" type="checkbox"/>		
Micro Care	Heavy Duty Degreaser C	100	100.13	<input checked="" type="checkbox"/>		
Micro Care	Flux Remover C	100	100.01	<input checked="" type="checkbox"/>		
3M	HFE 7100	100	94.64	<input checked="" type="checkbox"/>		
3M	HFE 7200	100	98.22	<input checked="" type="checkbox"/>		
Enviro Tech International Inc	Ensolv A	100	99.99	<input checked="" type="checkbox"/>		
Kyzen Corporation	Metalnox M6960	100	100.47	<input checked="" type="checkbox"/>		
Poly Systems USA Inc	Solvon Kreussler PB	100	99.80	<input checked="" type="checkbox"/>		
Poly Systems USA Inc	Solvon Kreussler IP	100	100.20	<input checked="" type="checkbox"/>		
Dow Chemical Company	OS 10	100	100.06	<input checked="" type="checkbox"/>		
Dow Chemical Company	OS 20	100	98.36	<input checked="" type="checkbox"/>		
Dow Chemical Company	OS 30	100	91.97	<input checked="" type="checkbox"/>		

Conclusion: All fourteen of the products removed over 85%.