

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2008  
 DateRun: 07/15/2008  
 Experimenters: Jason Marshall, Heidi Wilcox, Shweta Bansal  
 ClientType: Tool Manufacturer  
 ProjectNumber: Project #1  
 Substrates: Steel  
 PartType: Part  
 Contaminants: Buffing/Polishing Compounds  
 Cleaning Methods: Ultrasonics  
 Analytical Methods: Visual

Purpose: To evaluate selected cleaner on parts contaminated with buffing compound.

Experimental Procedure: Five products were diluted to 3% using DI water in a 1510 Branson 40 kHz ultrasonic tank and heated to 130 F. The products were degassed for five minutes.  
 A set of three soiled steel parts coated with buffing compound were immersed into the ultrasonic tank and cleaned for 5 minutes. Following cleaning, coupons were observed for cleanliness without a rinsing.  
 A second set of parts were cleaned at 160 F.

Results: All parts cleaned were equally cleaned after five minutes of cleaning at both temperatures. Some water spots were visible on all parts, but no buffing compound residue remained.

Summary:

<b>Substrates:</b>	Steel					
<b>Contaminants:</b>	Buffing/Polishing Compounds					
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>	
US Polychem Corporation	Polyspray Jet 790 XS	3	0.00	<input checked="" type="checkbox"/>		
BCS Company	Green Spray 400	3	0.00	<input checked="" type="checkbox"/>		
Magnaflux	Daraclean 282 GF	3	0.00	<input checked="" type="checkbox"/>		
Magnaflux	Daraclean KX 49	3	0.00	<input checked="" type="checkbox"/>		
Matchless Metal Polish Company	Buffclean 125 L	3	0.00	<input checked="" type="checkbox"/>		

Conclusion: Any of the five products could be used successfully to remove the buffing compound from the steel parts using ultrasonic cleaning.