

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004

DateRun: 07/06/2004

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Oil

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min. immersion cleaning at 96 F with stir-bar agitation  
NO Rinsing  
Drying: 30 sec. Air blow off using hose  
Contaminant:  
Oil Hall Company Plashall ESO Cas# 8013-07-8  
Substrate 2 " x 2" aluminum coupons

## Results:

### Summary:

<b>Substrates:</b>		Aluminum			
<b>Contaminants:</b>		Oil			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Petroferm Inc	Lenium ES	100	99.72	<input checked="" type="checkbox"/>	
Invista S.a.r.l	Flexisolv DBE 6 ester	100	99.71	<input checked="" type="checkbox"/>	

Conclusion: All were effective.