

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2007

DateRun: 05/22/2007

Experimenters: Shweta Bansal

ClientType: Lab

ProjectNumber: Project #1

Substrates: Brass

PartType: Coupon

Contaminants: Oil

Cleaning Methods: Ultrasonics

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min. Ultrasonics cleaning at 130 F  
Rinsing with Tap Water  
Drying: 30 sec. Air blow off using hose  
Contaminant  
3:1 nPB/Supercoat  
Substrate 2"x 4"x 0.06" Brass Coupons

## Results:

### Summary:

<b>Substrates:</b>		Brass				
<b>Contaminants:</b>		Oil				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>	
Finger Lakes Chemical	FLSC-12 Resineater Sample	100	-19.81	<input type="checkbox"/>		
Florida Chemical Company	Citrus Burst 7	100	-48.77	<input type="checkbox"/>		
Kyzen Corporation	Ionox HC 2	100	28.07	<input type="checkbox"/>		

### Conclusion: