

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2007

DateRun: 05/25/2007

Experimenters: Shweta Bansal

ClientType: Lab

ProjectNumber: Project #1

Substrates: Brass

PartType: Coupon

Contaminants: Oil

Cleaning Methods: Ultrasonics

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Cleaning: 5 min. Ultrasonics cleaning at 130 F.
Rinsing with Tap Water
Drying: 30 s50 Air blow off using hose
Contaminant
3:1 nPB/Supercoat
Substrate 2"x 4"x 0.06" Brass Coupons

Results:

Summary:

Substrates:	Brass				
Contaminants:	Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Kyzen Corporation	Ionox HC 2	5	62.15	<input type="checkbox"/>	
Phase III Inc	California Parts Washer Solution	5	5.03	<input type="checkbox"/>	
Florida Chemical Company	Citrus Burst 7	5	-15.93	<input type="checkbox"/>	

Conclusion: