CLEANING LABORATORY EVALUATION SUMMARY

SCL #:	2007
DateRun:	06/24/2007
Experimenters:	Shweta Bansal
ClientType:	Lab
ProjectNumber:	Project #1
Substrates:	Steel
PartType:	Coupon
Contaminants:	Greases
Cleaning Methods:	Ultrasonics
Analytical Methods:	Gravimetric
Purpose:	Laboratory evaluations of alternative cleaning products
Experimental Procedure:	Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Cleaning: 5 min. Ultrasonics cleaning at 130 F. Rinsing with Tap Water Drying: 30 s50 Air blow off using hose and outlet on bench Contaminant Premium Red Grease Substrate 2"x 4"x 0.06" Steel Coupons
Results:	
Summary:	

Substrates:	Steel				
Contaminants:	Greases				
Company Name:	**Product Name:**	**Conc.:**	**Efficiency:**	**Effective:**	**Observations:**
Gemtek Products	SC Aircraft & Metal Cleaner Super Concentrate	5	-3.55	☐	
Brulin Corporation	Aquavantage 3800 GD	5	-1.97	☐	
International Products Corporation	Micro 90 Conc.	5	-1.20	☐	

Conclusion: