

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2007

DateRun: 09/12/2007

Experimenters: Shweta Bansal

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Greases

Cleaning Methods: Ultrasonics

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min Ultrasonics cleaning at 130 F with stir-bar agitation.  
Rinsing with Tap Water  
Drying: 30 s50 Air blow off using hose and outlet on bench  
Contaminant  
Liqui lube  
Substrate 2"x 4"x 0.06" Aluminum Coupons

## Results:

### Summary:

<b>Substrates:</b>		Aluminum				
<b>Contaminants:</b>		Greases				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>	
Gemtek Products	SC Aircraft & Metal Cleaner Super Concentrate	5	96.63	<input checked="" type="checkbox"/>		
Valtech Corporation	Valtron SP 2275	5	97.68	<input checked="" type="checkbox"/>		
Brulin Corporation	Aquavantage 3800 GD	5	98.87	<input checked="" type="checkbox"/>		
Oakite Products	Inproclean 3800	5	99.81	<input checked="" type="checkbox"/>		

### Conclusion: